



Test Report # **PRECIOUSCALF-111725**

TOWNSEND LEATHER NFPA 260 COVER FABRIC BURN REPORT

Date: **11/17/2025**

Conditioning Chamber: Time In: 3:02 AM

Time Out: 6:10 AM

11/13/2025

11/17/2025

THICKNESS: 1.0 - 1.2 MM

Specimen: **Townsend Leather**

Precious Calfskin

Standard Filling Material: Non FR polyurethane foam, density 20 kg/m³ to 25 kg/m³
Test

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
1	SE	5.08
2	SE	10.16
3	SE	10.16

Retest

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
1	SE	5.08
3	SE	12.70

CLASS I ☒

CLASS II ☐

Tested according to NFPA 260 : 2013 Edition-Section 6.1 Cover Fabric Test

May Issa

Quality Control

Townsend Leather Co. Inc.

45-49 Townsend Ave PO Box 669

PO Box 669

Johnstown, NY 12095

This form is electronically signed. If you need an actual signature, please call.